

Silopren^{*} LSR 2255 TP 3562

Product Description **Silopren LSR 2255 TP 3562** is a flame retardant two-component liquid silicone rubber for injection moulding processes.

Key Performance Properties Vulcanizates consisting of **Silopren LSR 2255 TP 3562** are distinguished by the following properties:

- low flammability (LOI > 32 according ASTM D 2863-70)
- low viscosity
- excellent thermal stability
- high stability and flexibility at low temperatures
- good rubber-like properties
- good resistance to mineral oils
- outstanding resistance to ageing
- excellent dielectric behaviour over a wide range of temperatures
- not readily combustible, does not melt or drip
- UL 94 V-0, file E224733, Momentive Performance Materials

Applications Because of the outstanding properties **Silopren LSR 2255 TP 3562** is particularly suitable for the production of the following articles: anode caps, spark plug boots and sealing elements.

Typical Product Data

		A- component	B- component
Colour		dark-grey	light-grey
Viscosity in Pas gamma = 10 s ⁻¹ at 20 ° C	DIN 53 018	300	300
The pot-life of the mixture of the two components (closed vessel) at 20 ° C is three days. Increased temperatures reduce the pot-life.			

Typical properties of the vulcanizate: Mixing ratio of components A : B = 1 : 1. Vulcanisation: 10 min/175 ° C			
Density	DIN 53 479 A	g/cm ³	1.40
Hardness	DIN 53 505	Shore A	58
Tensile strength	DIN 53 504 S2	N/mm ²	5.7
Elongation at break	DIN 53 504 S2	%	360
Tear strength	ASTM D 624 die B	N/mm	17
Comp. Set 22h at 175°C	ISO 815	%	25
Volume resistivity	DIN 53482	ohm · cm	1.10 ¹⁵
Dielectric strength	DIN 53481	kV/mm	25
Dielectric constant	DIN 53483 (50 Hz)		3.5
Dissipation factor	DIN 53483 (50 Hz)		0.002

Specifications Typical product data should not be used as specifications. Assistance and specifications are available by contacting Momentive Performance Materials.

Containers **Silopren LSR 2255 TP 3562** is available in 20 kg pails and 200 kg drums.

Instructions for Use Ready-to-use mixtures (of the components A and B) are fed directly to the injection-moulding machine from the original containers by means of a metering and mixing unit. The mixture, consisting of the two components in the ratio 1:1, is injected into the heated mould. At mould temperatures of 170 - 230 ° C, the addition-curable silicone rubber vulcanises free of by-products within a few seconds. High curing speed and ease of demoulding permit fully automated production of large numbers of articles in short cycle times.
Silopren LSR 2255 TP 3562 should only be used for the production of technical articles for electrical applications.
Due to the special composition of **Silopren LSR 2255 TP 3562** this grade shows more abrasive properties than standard grades. Therefore it is recommended to use especially hardened equipment.

Handling and Safety Material Safety Data Sheets are available upon request from Momentive Performance Materials.

Storage Period Correctly stored in its original unopened container at room temperature (max. 27°C). **Silopren LSR 2255 TP 3562** has a shelf life of 540** days from the date of manufacturing. Containers, which have been opened, must be kept tightly closed afterwards.
**Please see also use-before/expiry date on product label and certificate.

Availability **Silopren LSR 2255 TP 3562** may be ordered from your regular sales contact or please call Momentive Performance Materials, Bergen-op-Zoom, Netherlands at 00800-4321-1000 to find out which is the nearest sales office to you.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	• Specialty Fluids	T 800.523.5862	F 304.746.1654
	• UA, Silanes, Resins, and Specialties	T 800.334.4674	F 304.746.1623
	• RTV Products-Elastomers	T 800.332.3390	F 304.746.1623
	• Sealants and Adhesives & Construction	T 877.943.7325	F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	• Argentina & Chile	T +54.11.4862.9544	F +54.11.4862.9544
	• Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	• Mexico & Central America	T +52.55.5899.5135	F +52.55.5899.5138
	• Venezuela, Ecuador, Peru, Colombia, & Caribbean	T +58.212.285.2149	F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
	E cs-ap.silicones@momentive.com		
Pacific	• Japan	T +81.276.20.6182	
	• China	T +86.21.5050.4666 (ext. 1523)	
	• Korea	T +82.2.6201.4600	
	• Singapore	T +65.6220.7022	
	Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.