

RTV 833

2 component addition cure material

Product Description RTV833 is a solvent-free, flowable - 2 Component tacky RTV Silicone rubber. After mixing the RTV833A and RTV833B at a mix ratio of 1:1 the material cures by an addition reaction at room temperature. The cure rate can be accelerated significantly by heat. Material has been specially developed as a tacky fabric coating.

- Key Performance Properties**
- Convenient 1:1 mixing
 - Free of solvents
 - Good self leveling characteristics
 - No by products released
 - Fast cure at elevated temperatures
 - Translucent

Applications RTV833 tacky silicone compound has been specially developed as a tacky coating for fabric. Typical applications include, but are not limited to, lace coating, clothes and conveyer belt coating. RTV833 can also be used for other applications where fast cure at elevated temperatures with a tacky surface and good flow or self-leveling characteristics are required.

Typical Product Data

Components	Unit	RTV833A	RTV833B
Appearance		Translucent	Translucent
Viscosity 20 °C	(Pa.s)	100	110
Mixed	Unit	RTV833A : RTV833B 1: 1	
Appearance		Translucent	
Pot Life at RT	(Minutes)	100	
Viscosity 20 °C	(Pa.s)	100	
Cured properties(24 hrs RT)		Method	Unit
Tensile Strength		DIN53504	(MPa) 0.7
Elongation		DIN53504	(%) 480
Hardness		DIN 53505	Shore 00 25
Modulus @ 100 % Elongation		DIN 53504	(MPa) 0.07

The above given values are based on material, which was produced in the pilot plant.

Specifications Typical product data values should not be used as specification. Assistance and specification are available by contacting Momentive performance materials Technical Service RTV1 and RTV2.

Instructions for Use

Mixing

Select a mixing container 4-5 times larger than the total volume of material to be mixed. Weigh out the RTV833A and RTV833B components (in a ratio of 1:1 by weight) optionally combined with a pigment paste (e.g. 1 or 2 % by weight of Silopren LSR colour batch). Stir for several minutes until the material is well mixed. The air entrapped in the mixing step needs to be removed. Exposing the material to an absolute pressure of 10-20 mbar will achieve this. The material will expand, crest and reduce to approximately its original level. Degassing is usually complete within about two minutes after frothing ceases.

Automatic equipment designed to meter, mix and dispense a two component silicone liquid rubber, with optionally a third system to dose and mix in the pigment, will add convenience to continuous large scale operations.

Compatibility

RTV833 will cure when applied to a clean, dry surface, which has been properly prepared. Certain materials such as butyl and chlorinated rubber, sulfur containing materials, amines and certain metal soap-cured RTV silicone rubber compounds, can cause cure inhibition.

It is recommended that a sample patch test will be performed with the RTV product to determine if a barrier coating or other inhibition preventing measure is necessary before applying the RTV833.

Curing

Thin coatings of RTV833 can be applied to the substrate by dipping, knife spreading or extrusion. Thin films can be cured within 2 minutes at 150 deg. C depending on coat weight and heat exchange efficiency. Thicker coatings will decrease the rate of heat transfer and will therefore require a longer cure time or higher cure temperature.

Bonding

Due to the excellent flow and penetration behavior of RTV833 mechanical bonding is obtained on most fabrics. If a stronger (chemical) bond is required, then the use of a primer will be needed. A suitable primer is SS4155 or SS4120. The surface of the substrate to be primed needs to be thoroughly cleaned. Cleaning should be done with a non-oily solvent such as MEK or IPA. The primer needs to be applied in a uniform thin layer on the cleaned surface. Allow the primer to dry for one hour or more. Apply the freshly mixed RTV833 to the primed surface and cure as recommended.

To confirm the bonding performance, it is recommended to do a small-scale adhesion test on the substrate.

Handling and Safety

Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for solvents and other chemicals used with the Momentive performance materials products should be obtained from your supplier. When solvents are used, proper safety precautions must be observed.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	• Specialty Fluids	T 800.523.5862	F 304.746.1654
	• UA, Silanes, Resins, and Specialties	T 800.334.4674	F 304.746.1623
	• RTV Products-Elastomers	T 800.332.3390	F 304.746.1623
	• Sealants and Adhesives & Construction	T 877.943.7325	F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	• Argentina & Chile	T +54.11.4862.9544	F +54.11.4862.9544
	• Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	• Mexico & Central America	T +52.55.5899.5135	F +52.55.5899.5138
	• Venezuela, Ecuador, Peru, Colombia, & Caribbean	T +58.212.285.2149	F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
	E cs-ap.silicones@momentive.com		
Pacific	• Japan	T +81.276.20.6182	
	• China	T +86.21.5050.4666 (ext. 1523)	
	• Korea	T +82.2.6201.4600	
	• Singapore	T +65.6220.7022	
Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131	F +607.786.8309

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.