



TSE325

TSE325

Description

TSE325 silicone adhesive is a one-component heat curable silicone adhesive designed for potting and encapsulation. This product adheres to many substrates without a primer and cures at elevated temperatures. This product has a very long working time at room temperature. TSE325 is a white, flowable material with self-leveling properties.

Key Features and Benefits

- One component products - no mixing required
- Cure at elevated temperature
- Low viscosity - easily pourable
- Primerless adhesion to many types of substrates
- No cure by-products, low linear shrinkage
- Non-corrosive to metals and sensitive substrates
- Outstanding performance over a wide temperature range

Typical Physical Properties

Uncured Properties		TSE 325
Colour		White
Viscosity	mPa-s	4000
Specific Gravity	g/cm ³	1.02
Cured Properties		(cured 1 hour at 150°C)
Durometer	Shore A	12
Elongation	%	200
Tensile Strength	MPa	0.7
Adhesion (Al to Al)	MPa	0.4
Dielectric Strength	kV/mm	21
Dielectric Constant		2.9
Dissipation Factor		0.001
Volume Resistivity	Ohm-cm	2 x 10 ¹⁵

Potential Applications

- Coating of hybrid IC's, printed circuit boards, etc
- Electrical potting and encapsulation
- General adhesive for many types of substrates

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

CAUTION

TSE325 silicone adhesive can generate flammable hydrogen gas upon contact with acidic, basic, or oxidizing materials. Such contact should be avoided.

The shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 4 month when stored in the original unopened containers between 0° and 10 °C

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

Compatibility

TSE325 silicone adhesive cures in contact with most clean, dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfurcontaining materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a gummy appearance of the TSE325 silicone adhesive at the interface between the adhesive and the substrate to be bonded. It is recommended that a sample patch test be performed with the TSE325 silicone adhesive to determine substrate compatibility.

Surface Preparation

The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of TSE325 silicone adhesive and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the adhesive.

Curing

TSE325 silicone adhesive requires elevated temperatures in order to achieve full cure. Typical cure times and temperatures are as follows:

Temperature	TSE 325
100°C	4 hours
120°C	2 hours
150°C	1 hour

The actual cure time is affected by such things as cross-sectional thickness of the TSE325 silicone adhesive, heat capacity of the overall assembly and efficiency and type of oven used (i.e. convection, infrared)

Adhesion capability

Suitable substratesMetals: Aluminium, Copper, Ni plate; Stainless steelPlastics: PPS, PBT, Epoxy resin, Polyester, Phenolic resinRubbers: Heat cured silicone rubberInorganics: Glass, Ceramics

Not suitable substratesPlastics: PP, PE, Fluorocarbon resinRubbers: Sulphur vulcanized rubbers, Fluorocarbon rubber

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Specifications

Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive Performance Materials Technical Service RTV1 and RTV2.

Availability

TSE325 is available in 1kg cans and 18.1 kg pails.

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of

innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

Contact Information For product prices, availability, or order placement, contact our customer service by visiting momentive.com/ContactSilicones.

For literature and technical assistance, visit our website at: www.momentive.com

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Holdings Inc.

DISCLAIMER The information provided herein was believed by Momentive Performance Materials Inc. ("Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Momentive are subject to Momentive's terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.