

TSE 3253

Flame retardant silicone adhesive

Product Description

TSE3253 is a one-component, semi-flowable, heat curable silicone adhesive designed for electrical and electronic applications. This product cures with heating in a short period of time to a tough silicone elastomer.

Key Performance Properties

- Flame resistant – approved UL94V-1 (File No: E56745)
- Semi-flowable consistency
- Excellent high and low temperature resistance
- Heat accelerated cure
- Easy to use – one component system
- Primerless adhesion to many substrates – Plastics, Metals, Ceramics and Glass
- Non corrosive to metals

Typical Applications

- Sealing, coating and potting for high voltage parts
- Adhesion and sealing for communications equipment

Typical Product Data

Typical uncured properties		
Appearance		semi-flowable
Colour		black
Viscosity	Pa·s	14

Typical Product Data

Typical cured properties (1hr @150°C)		
Density	g/cm ³	1.22
Hardness	Shore A	30
Tensile strength	MPa	2.9
Elongation	%	200
Adhesive strength (Aluminium Lap shear)	MPa	1.0
Thermal conductivity	W/ m·K	0.18
Volume resistivity	ohm·cm	7·10 ¹⁵
Dielectric strength	kV/mm	23

Dielectric constant @ 60Hz		3,0
Dissipation factor @ 60Hz		0.004
Linear expansion	1/K	$2.1 \cdot 10^{-4}$

Adhesion capability

Suitable substrates:

Metal: Aluminium, Copper, Ni plated, Stainless Steel
 Plastics: PPS, PBT, Epoxy resin, Polyester, Phenolic resin
 Rubbers: Heat cured silicone rubber
 Inorganics: Glass, Ceramics

Not suitable substrates:

Plastics: PP, PE, Fluorocarbon resin
 Rubbers: RTV silicone rubber, Sulphur vulcanized rubber, Fluorocarbon rubber

Instruction for use

TSE 3253 is a single component addition-curing ready to use adhesive. Materials such as water, sulphur, nitrogen compounds, organic metallic salts, phosphorous compounds, etc. contained in the surface of the substrate can inhibit curing. A sample patch should always be conducted before proceeding to determine compatibility.

Before using the product, allow the contents to return to room temperature before opening the container to avoid condensation.

Handling and Safety

Material and Safety Data Sheets are available upon request from Momentive performance materials. Similar information from solvents and other chemicals used with the Momentive performance materials products should be obtained from the supplier. When solvent is used, proper safety precautions must be observed.

Storage and Warranty Period

The shelf life from the material will be indicated by the "use before date" on the associated documents with a minimum of 4 months when stored in unopened containers at 10°C or less.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	• Specialty Fluids	T 800.523.5862	F 304.746.1654
	• UA, Silanes, Resins, and Specialties	T 800.334.4674	F 304.746.1623
	• RTV Products-Elastomers	T 800.332.3390	F 304.746.1623
	• Sealants and Adhesives & Construction	T 877.943.7325	F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	• Argentina & Chile	T +54.11.4862.9544	F +54.11.4862.9544
	• Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	• Mexico & Central America	T +52.55.5899.5135	F +52.55.5899.5138
	• Venezuela, Ecuador, Peru, Colombia, & Caribbean	T +58.212.285.2149	F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
	E cs-ap.silicones@momentive.com		
Pacific	• Japan	T +81.276.20.6182	
	• China	T +86.21.5050.4666 (ext. 1523)	
	• Korea	T +82.2.6201.4600	
	• Singapore	T +65.6220.7022	
Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131	F +607.786.8309

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS.

EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.