



SilCool* XE13-C1862

SilCool* XE13-C1862

Description

XE13-C1862PT is a one-component, heat curable silicone adhesive designed for thermally conductive applications. The product cures quickly with heat and adheres well to a variety of substrates without the use of a primer.

Key Features and Benefits

- Excellent thermal conductivity
- Low viscosity
- Higher elongation than conventional products
- Ready to use: one component
- Heat accelerated cure
- Excellent adhesive properties: Primerless adhesion to many types of substrates
- Non corrosive to metals

Typical Physical Properties

(JIS K 6249)	
UNCURED PROPERTIES	
Appearance	Gray, flowable paste
Viscosity (23°C) Pa·s	50
CURED PROPERTIES (1h @ 150°C)	
Density (23°C) g/cm ³	2.87
Hardness (Type A)	64
Tensile strength MPa {kgf/cm ² }	1.4 {14}
Elongation %	80
Adhesive strength ^{*1} MPa {kgf/cm ² }	0.9 {9}
Linear expansion ^{*2} 1/K	1.3x10 ⁻⁴
Thermal Conductivity ^{*3} W/(m·K)	2.5
Thermal resistance ^{*4} (50µm) mm ² K/W	25
Glass transition point °C	-120
Volume resistivity Ω·cm	5.0x10 ¹⁴
Dielectric strength kV/mm	20

Ionic impurities*5 ppm	Na+	<5
	K+	<5
	Cl-	<5
Water adsorption*2 %		<0.6

*1: Aluminum lap shear *2: In-house test method *3: Hot wire

*4: Laser flash analysis on a Si-Si sandwiched material *5: Ion chromatography analysis

Typical property data values should not be used as specifications.

Potential Applications

- Sealing and bonding for thermally conductive applications- Heat generating elements, Regulators, Rectifier, Thyristor, etc.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

- Store at cool temperature (0–10°C) to prevent a viscosity increase. When returning to room temperature, allow the contents to return to room temperature before opening the container to avoid condensation.
- Keep out of the reach of children.

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

- Materials such as water, sulfur, nitrogen compounds, organic metallic salts, phosphorus compounds, etc. contained in the surface of the substrate can inhibit curing. A sample patch should always be conducted before proceeding to determine compatibility.
- All parts should be as clean and dry as possible prior to application
- Wear eye protection and protective gloves as required when handling this product.
- Maintain adequate ventilation in the work area at all times.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Packaging

- 333ml cartridge available in cases of 10

From automotive to healthcare, from electronics to construction, products from Momentive Performance Materials Inc. are practically everywhere you look. We are a global leader in silicones and advanced materials with a 70+ year heritage of innovation and being first to market – with performance applications that improve everyday life. By knowing our customers' needs and creating custom technology platforms for them, we provide science based solutions to help customers increase performance, solve product development issues and engineer better manufacturing processes.

Contact Information For product prices, availability, or order placement, contact our customer service by visiting momentive.com/ContactSilicones.

For literature and technical assistance, visit our website at: www.momentive.com

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Holdings Inc.

DISCLAIMER The information provided herein was believed by Momentive Performance Materials Inc. ("Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Momentive are subject to Momentive's terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE.** except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.